

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁴ : C08F 299/04, C08J 3/10 C08L 67/06 // C03C 25/02	A1	(11) International Publication Number: WO 87/ 02371 (43) International Publication Date: 23 April 1987 (23.04.87)
(21) International Application Number: PCT/US86/01875 (22) International Filing Date: 12 September 1986 (12.09.86) (31) Priority Application Number: 789,887 (32) Priority Date: 21 October 1985 (21.10.85) (33) Priority Country: US (71) Applicant: OWENS-CORNING FIBERGLAS CORPORATION [US/US]; Fiberglas Tower 26, Toledo, OH 43659 (US). (72) Inventors: BRANNON, Robert, Clifford ; 613 Moull Street, Newark, OH 43055 (US). COLEMAN, David, Alan ; 53 Edgemill Drive, Newark, OH 43055 (US). MILLER, David, George ; 42 Aspen Lane SW, Pataskala, OH 43062 (US).		(74) Agents: HUDGENS, Ronald, C. et al.; Fiberglas Tower 26, Toledo, OH 43659 (US). (81) Designated States: AU, BE (European patent), DE (European patent), FR (European patent), IT (European patent), JP, NL (European patent). Published <i>With international search report.</i>
(54) Title: POLYESTER EMULSION (57) Abstract A cure stable polyester emulsion for use in an aqueous size composition has been developed for glass fibers produced for molded products having appearance surfaces known as Class A surfaces. The emulsion consists essentially of an unsaturated polyester resin emulsified with nonylphenoxypoly (ethyleneoxy) ethanol. The size contains this cure stable unsaturated polyester emulsion and a static insensitive lubricant system. The resulting coated glass fibers are especially useful in improving processability and product uniformity of SMC application.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	ML	Mali
AU	Australia	GA	Gabon	MR	Mauritania
BB	Barbados	GB	United Kingdom	MW	Malawi
BE	Belgium	HU	Hungary	NL	Netherlands
BG	Bulgaria	IT	Italy	NO	Norway
BJ	Benin	JP	Japan	RO	Romania
BR	Brazil	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	LI	Liechtenstein	SN	Senegal
CH	Switzerland	LK	Sri Lanka	SU	Soviet Union
CM	Cameroon	LU	Luxembourg	TD	Chad
DE	Germany, Federal Republic of	MC	Monaco	TG	Togo
DK	Denmark	MG	Madagascar	US	United States of America
FI	Finland				

1

-1-

5

D E S C R I P T I O N

POLYESTER EMULSION

10

TECHNICAL FIELD

This invention relates to polyester emulsions. The emulsions are intended for size compositions for glass fibers which may be incorporated into molding compounds.

BACKGROUND ART

15

The use of unsaturated polyester compounds in combination with thermoplastic resins and fillers to produce molding compositions is well known. These compositions, intended to polymerize when molded under heat and pressure, are generally combined with fillers and chopped glass, produced from roving, to produce molded products having appearance surfaces with a minimum of irregularities or undulations known as Class A surfaces.

20

The use of chopped glass as reinforcement in such molding compounds is well known. The chopped glass is produced in the form of individual strands which are sized, gathered into rovings, chopped to the desired length and incorporated into the resin composite prior to molding.

25

The sizes generally comprise a polyester emulsion base, a lubricant, film formers and the like and are extremely important in imparting to the reinforcing glass its ability to be wetted out by the molding compound. These sizes are also important in that they protect the glass in its handling subsequent to being sized and are influential in minimizing the amount of fuzz and fly which is produced on the glass, the fuzz and fly having a decided affect upon the appearance surface of the molded product.

30

35

-2-

1 The sized glass fibers generally are employed as reinforcement for sheet molding compounds (SMC) and bulk molding compounds (BMC).

DISCLOSURE OF INVENTION

5 According to this invention, we have provided an improved polyester emulsion for polyester-based sizes. We have a cure stable polyester emulsion for these sizes. The resulting formulation provides for very low static generation which allows antistatic methods to work better
10 even at low relative humidity. The sized glass fibers are particularly suitable for use in sheet molding compounds.

 Unsaturated polyesters useful in this invention typically contain a polyesterification product of one or more ethylenically unsaturated dicarboxylic acids or
15 anhydrides such as maleic or fumaric with one or more glycols such as ethylene or propylene glycol and, sometimes, minor proportions of other aromatic or aliphatic mono- or dicarboxylic acids or anhydrides and/or other mono- or polyhydroxyl compounds. They also typically contain an
20 ethylenically unsaturated monomer, such as styrene, copolymerizable with the unsaturated polyester for curing.

BRIEF DESCRIPTION OF THE DRAWINGS

 FIG. 1 is a graph showing surfactant stability as measured by isothermal thermogravimetric weight loss.

25 FIG. 2 is a graph showing acetone solubility through the forming cake.

 FIG. 3 shows electrostatic data obtained from the size of Example 1.

 FIG. 4 shows electrostatic data obtained from the
30 control size of Example 2.

BEST MODE OF CARRYING OUT THE INVENTION

 The unsaturated polyesters are primarily polyesterification products of an ethylenically unsaturated dicarboxylic acid or anhydride such as maleic acid or
35 anhydride (which will ordinarily and preferably be at least partially isomerized to the fumarate form during the polyesterification) and a glycol such as ethylene or

-3-

1 propylene glycol or the corresponding epoxide. Minor molar proportions of other acid and/or hydroxyl reactants can be incorporated, if desired, according to generally accepted practice. For example, the reactivity of the polyester in
 5 the addition copolymerization reaction involved in curing can be reduced by substituting a dicarboxylic acid or anhydride not having any ethylenic unsaturation for a minor molar proportion of the ethylenically unsaturated dicarboxylic acid or anhydride. Either aliphatic or
 10 aromatic substitutes may be employed, the most common probably being isophthalic acid. Minor molar proportions of monofunctional carboxylic acid or alcohol reactants can also be incorporated; these can serve not only to modify the reactivity of the resultant polyester and its compatibility
 15 with other size components but can also be employed to control its acid and/or hydroxyl value independently of its average molecular weight.

The cure stable polyester emulsion is a conventional unsaturated polyester emulsified with
 20 nonylphenoxypoly (ethyleneoxy) ethanol. One such material is Igepal CO-997 from GAF. This surfactant does not degrade during drying and does not interfere with the cure of the polyester resin.

This invention may be used in an aqueous size
 25 composition comprising, approximately, on a weight percent basis:

	<u>Weight Percent</u>
Cure, stable polyester emulsion	50 - 55
Polyvinylacetate copolymer	40 - 45
30 Glacial acetic acid	0 - 0.3
Silane	2 - 4
Static insensitive lubricant	0.05 - 2
Wax	0 - 3
Water	Balance
35 Final solids content ranges from 10 to 15 percent. The sizing composition is applied so as to deposit a dried size	

-4-

1 coating on the fibers corresponding to about 0.2 to 3.0 weight percent of the weight of the fibers (LOI).

Preferably, the size composition is prepared according to the following formulation:

5		<u>Weight Percent</u>
	Cure, stable polyester emulsion	51.5 - 53.5
	Polyvinylacetate copolymer	41.5 - 43.5
	Glacial acetic acid	0 - 0.3
	Silane	2 - 3
10	Static insensitive lubricant	0.05 - 1
	Wax	0 - 2
	Water	Balance

Preferably, final solids content ranges from 11 to 14 percent. The sizing composition is applied so as to deposit
 15 a dried size coating on the fibers corresponding to about 0.2 to 2 weight percent of the weight of the fibers (LOI).

The control resin used in the following examples is a conventional unsaturated polyester emulsified with a block co-polymer of polyoxyethylene and polyoxypropylene.
 20 One such material is Pluronic^R F-77 from BASF.

Both the cure stable polyester emulsion of this invention, CX1717 from Owens-Corning Fiberglas, and the control polyester emulsion of Example II, CX412 from Owens-Corning, are prepared from Owens-Corning E-400
 25 polyester resin. E-400 is a conventional polyester resin prepared from phthalic anhydride (26%), maleic anhydride (17%), propylene glycol (28%) and styrene (27%). The balance being CO-997 for the present invention versus F-77 for the control emulsion, and very small amounts of
 30 toluhydroquinone and p-benzoquinone inhibitors.

The emulsification procedure that was used is as follows. The E-400 resin is charged to a mixer fitted with a chiller. The chiller is turned on before the resin is charged. Next, the surfactant (emulsifier) is added.
 35 Igepal CO-997 must be heated to a pourable liquid before adding. The resin and surfactant are mixed for 1 hour at a high shear of 700 and a sweep of 10. Water addition then is

-5-

1 carried out to achieve a desired solids content. After
process is complete, allow batch to mix ten (10) minutes
then take sample for particle size and solids. Solids and
viscosity are finally adjusted by water addition. When
5 batch is in specification, sample is ready.

The static insensitive lubricant is a combination
of cocoa amine acetate and a polyethyleneimine. We selected
this chemistry to obtain low fuzz during SMC processing
without affecting cure of the polyester or PVAC film
10 formers.

The pH of the size typically ranges from 2 to 4
and preferably is about 3.

Example I

A size composition using the inventive polyester
15 emulsion was prepared from the following ingredients.

		<u>Weight Percent</u>
	Cure stable polyester emulsion; CX1717 from Owens-Corning Fiberglas	52.31
20	Polyvinylacetate copolymer; National Starch 25-2828	42.80
	Gamma-methacryloxy- propyltrimethoxysilane;	2.94
25	Union Carbide A-174	
	Cocoa amine acetate;	0.25
	Alkaril PF-710	
30	Polyethyleneimine; Emery 6760u	0.25
	Carbowax; Union Carbide C-1000	1.45
	Deionized water	Balance

35 Final solids content was about 14 weight percent. The
sizing composition is applied so as to deposit a dried size

-6-

- 1 coating on the fibers corresponding to about 2 weight percent of the weight of the fibers (LOI).

Example II (Control)

- 5 A control size composition was prepared from the following ingredients.

		<u>Weight Percent</u>
	Conventional polyester emulsion;	64.33
	Owens-Corning Fiberglas 412	
10	Polyvinylethylene emulsion;	15.20
	Air Products A400	
	Polyvinylacetate copolymer;	13.98
	National Starch 25-2828	
15	Gamma-methacryloxy-	2.85
	propyltrimethoxysilane;	
	Union Carbide A-174	
20	Cirrasol 185AEAN pelargonic	2.22
	acid and tetraethylenepentamine	
	Carbowax; Union Carbide C-1000	1.41
25	Deionized water	Balance

The percent solids in the size composition was about 13. The strand solids corresponded to about 2 weight percent of the weight of the fibers (LOI).

INDUSTRIAL APPLICABILITY

30

Example III

- The size of Example I and the control size of Example II were prepared by conventional size preparation methods and applied to the glass strand using conventional application techniques. The incorporation of the sized strands into the resin composition is performed by conventional methods.

-7-

1 Glass fibers used in the practice of this invention can be, but are not restricted to, "E" glass fibers, well known to those skilled in the art. Such fibers are described in U.S. Patent No. 2,334,961.

5 Strands of glass fibers are produced by pulling several hundred or more tiny molten streams of glass which issue from holes in the bottom of a bushing over a size applying apron to a gathering shoe which groups the fibers together into a strand. This strand then proceeds to a
10 traverse mechanism and winding drum which provides the pulling action which attenuates the molten glass and coils the strand into a package. The fibers are individually separated at the time that they pass over the size applicator, so that the surfaces of the fibers are
15 substantially completely coated before they are drawn together into a strand. This size acts as a lubricant which separates the individual filaments, and if the filaments are not separated by the size, they will scratch each other and break as they are flexed and drawn over guide eyes or other
20 contact surfaces in subsequent operations such as roving or SMC compounding.

Example IV

Glass fibers coated with the size of Example I and the control size of Example II were compared as follows.

25 FIG. 1 shows the thermal stability in air of Igepal^R CO-997 vs. control F-77 surfactant. The inventive surfactant only loses about 8 to 10% solids over 17.5 hours at 130°C (265°F). The control surfactant lost about 92% solids under the same conditions.

30 FIG. 2 shows the acetone solubility for the sized glass fibers of this invention vs. the control product dried over 13 hours at 130°C (265°F). The inventive size consistently had lower solubility at various positions through the forming cake. Consistency of cure through the
35 forming cake is due to the improved thermal stability of CO-997 surfactant relative to F-77. The forming cakes are terms used to identify strands of sized glass fibers prior

-8-

1 to further finishing operations. The effectiveness of the Igepal^R surfactant in controlling solubility and cure of the polyester film former is apparent from this data.

Electrostatic properties were obtained on forming
5 cakes made from each of the sizes in Examples I and II. In this test, a single strand from a forming cake is triboelectrically charged by a constant friction device and monitored for residual charge with an electrostatic probe. Both generation and dissipation mechanisms are characterized
10 by this method. The monitored charge is converted to a relative frequency histogram, which includes several strands from the same forming cake.

The static data for Examples I and II are shown in Figures 3 and 4, respectively. The inventive product
15 reduces the amount of highly charged negative surface potential. This results in a more narrow charge distribution and a nominal charge which is closer to zero. Both of these factors improve static performance during SMC processing. Static buildup on chopper surfaces is reduced,
20 and uniformity of the chopped glass bed is improved.

25

30

35

-9-

1

5

C L A I M S

1. Cure stable polyester emulsion consisting
10 essentially of an unsaturated polyester resin emulsified
with nonylphenoxypoly (ethyleneoxy) ethanol.

2. Polyester emulsion according to claim 1 having
an amount of the ethanol ranging from 2 to 20 weight percent
based on the weight of resin.

15 3. Polyester emulsion according to claim 1 having
an amount of the ethanol ranging from 2 to 5 weight percent
based on the weight of resin.


4. Polyester emulsion according to claim 1
wherein the polyester resin comprises ethylenically
20 unsaturated polyester and ethylenically unsaturated monomer
copolymerizable with the polyester.

5. Polyester emulsion according to claim 4
wherein the unsaturated polyester is prepared from
ethylenically unsaturated dicarboxylic acid or anhydride and
25 glycol or corresponding epoxide.

6. Polyester emulsion according to claim 4
wherein the polyester resin is prepared from phthalic
anhydride, maleic anhydride, propylene glycol and styrene.


30



35



SURFACTANT STABILITY *FIG. 1*

FIG. 2





INTERNATIONAL SEARCH REPORT

International Application No PCT/US 86/01875

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ⁶ According to International Patent Classification (IPC) or to both National Classification and IPC IPC ⁴ : C 08 F 299/04; C 08 J 3/10; C 08 L 67/06; //C 03 C 25/02																	
II. FIELDS SEARCHED <div style="text-align: center; border-top: 1px solid black; border-bottom: 1px solid black; margin: 5px 0;">Minimum Documentation Searched ⁷</div> <table style="width: 100%; border-collapse: collapse;"> <tr> <th style="width: 25%; border-bottom: 1px solid black;">Classification System</th> <th style="border-bottom: 1px solid black;">Classification Symbols</th> </tr> <tr> <td style="padding: 5px;">IPC⁴</td> <td style="padding: 5px;">C 08 F; C 08 J; C 08 L; C 03 C; D 06 M</td> </tr> </table> <div style="text-align: center; border-top: 1px solid black; border-bottom: 1px solid black; margin: 5px 0;">Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸</div>			Classification System	Classification Symbols	IPC ⁴	C 08 F; C 08 J; C 08 L; C 03 C; D 06 M											
Classification System	Classification Symbols																
IPC ⁴	C 08 F; C 08 J; C 08 L; C 03 C; D 06 M																
III. DOCUMENTS CONSIDERED TO BE RELEVANT ⁹ <table style="width: 100%; border-collapse: collapse;"> <tr> <th style="width: 10%; border-bottom: 1px solid black;">Category ⁹</th> <th style="width: 70%; border-bottom: 1px solid black;">Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²</th> <th style="width: 20%; border-bottom: 1px solid black;">Relevant to Claim No. ¹³</th> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">P,X</td> <td style="padding: 5px;">EP, A, 0181839 (SOGIMI) 21st May 1986, see claims 1-10; page 6, lines 8-16; examples 4-9 --</td> <td style="text-align: center; vertical-align: top; padding: 5px;">1-6</td> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">X</td> <td style="padding: 5px;">US, A, 3440193 (P.J. CAMPAGNA) 22 April 1969, see column 2, lines 3-35; column 3, line 3 - column 4, line 2; column 4, lines 17-57; examples 1-10 --</td> <td style="text-align: center; vertical-align: top; padding: 5px;">1-3</td> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">X</td> <td style="padding: 5px;">DE, A, 2903022 (BAYER) 31 July 1980, see claims --</td> <td style="text-align: center; vertical-align: top; padding: 5px;">1-3</td> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">A</td> <td style="padding: 5px;">GB, A, 1434448 (OWENS-CORNING FIBERGLAS) 5 May 1976 -----</td> <td></td> </tr> </table>			Category ⁹	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³	P,X	EP, A, 0181839 (SOGIMI) 21st May 1986, see claims 1-10; page 6, lines 8-16; examples 4-9 --	1-6	X	US, A, 3440193 (P.J. CAMPAGNA) 22 April 1969, see column 2, lines 3-35; column 3, line 3 - column 4, line 2; column 4, lines 17-57; examples 1-10 --	1-3	X	DE, A, 2903022 (BAYER) 31 July 1980, see claims --	1-3	A	GB, A, 1434448 (OWENS-CORNING FIBERGLAS) 5 May 1976 -----	
Category ⁹	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³															
P,X	EP, A, 0181839 (SOGIMI) 21st May 1986, see claims 1-10; page 6, lines 8-16; examples 4-9 --	1-6															
X	US, A, 3440193 (P.J. CAMPAGNA) 22 April 1969, see column 2, lines 3-35; column 3, line 3 - column 4, line 2; column 4, lines 17-57; examples 1-10 --	1-3															
X	DE, A, 2903022 (BAYER) 31 July 1980, see claims --	1-3															
A	GB, A, 1434448 (OWENS-CORNING FIBERGLAS) 5 May 1976 -----																
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p>¹⁰ Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"Z" document member of the same patent family</p> </div> </div>																	
IV. CERTIFICATION <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black; padding: 5px;">Date of the Actual Completion of the International Search</td> <td style="width: 50%; border-bottom: 1px solid black; padding: 5px;">Date of Mailing of this International Search Report</td> </tr> <tr> <td style="padding: 5px;">4th December 1986</td> <td style="text-align: center; padding: 5px;">21 JAN 1987</td> </tr> <tr> <td style="border-bottom: 1px solid black; padding: 5px;">International Searching Authority</td> <td style="border-bottom: 1px solid black; padding: 5px;">Signature of Authorized Officer</td> </tr> <tr> <td style="text-align: center; padding: 5px;">EUROPEAN PATENT OFFICE</td> <td style="text-align: center; padding: 5px;">VAN MOL </td> </tr> </table>			Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	4th December 1986	21 JAN 1987	International Searching Authority	Signature of Authorized Officer	EUROPEAN PATENT OFFICE	VAN MOL							
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report																
4th December 1986	21 JAN 1987																
International Searching Authority	Signature of Authorized Officer																
EUROPEAN PATENT OFFICE	VAN MOL																

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON

INTERNATIONAL APPLICATION NO. PCT/US 86/01875 (SA 14541)

This Annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on 11/12/86

The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A- 0181839	21/05/86	None	
US-A- 3440193	22/04/69	NL-A- 6606104 BE-A- 680595 FR-A- 1478892	07/11/66 17/10/66
DE-A- 2903022	31/07/80	None	
GB-A- 1434448	05/05/76	None	

For more details about this annex :
see Official Journal of the European Patent Office, No. 12/82